Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-07-06-22** **Date: 15-03-2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/105/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-03-2019
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	13-03-2019
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.13%	_
2	Finess by Air permeablity method (m^2/kg,Min)	281.1	225m^2/kg, Min
3	Density (gm/cc)	3.13	_
4	Standard Consistency (%)	28.0%	Not specified
5	Initial Setting time	170 minutes	Not less than 30 minutes
6	Final Setting time	290 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-07-06-22** **Date: 10-04-2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/105/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-03-2019
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	13-03-2019
Environmental Conditions during test	:	Temperature: 26˚C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.0N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.0N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-07-06-22** **Date: 15-03-2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/105/18-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	12-03-2019
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-03-2019

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	1210	1210	8.1	91.9	90-100
3	20 mm	5328	6538	43.6	56.4	30-70
4	10 mm	6251	12789	85.3	14.7	10-35
5	4.75 mm	1641	14430	96.2	3.8	0-5
6	Pan	570	15000	100.0	0	---

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-07-06-22** **Date: 15-03-2019**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**12.4**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.1**	
3	Specific Gravity	**2.63**	_
4	Bulk Density(Loose) (Kg/l)	**1.47**	_
5	Bulk Density(Compacted) (Kg/l)	**1.51**	_
6	Water Absorption(%)	**0.22**	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

ASSt. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-07-06-22** **Date: 14-03-2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.
Customer Reference	:	EE(Project)/Ynk Zone/WO/105/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-03-2019
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-03-2019

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	219	219	4.4	95.6	90-100
3	10 mm	2853	3072	61.4	38.6	25-55
4	4.75 mm	1732	4804	96.1	3.9	0-10
5	Pan	196	5000	100	0	–

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL Pro
Sig.....
Date.....
BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-07-06-22** **Date: 14-03-2019**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.5	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.9	
3	Specific Gravity	2.63	_
4	Bulk Density(Loose) (Kg/l)	1.41	_
5	Bulk Density(Compacted) (Kg/l)	1.45	_
6	Water Absorption(%)	0.21	_
7	Aggregate crushing Value(%)	22.3	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.2	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-07-06-22** **Date: 14-03-2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Community Property Maintenance Including Parks in Ward No.03.

Agency : Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.

Customer's Reference : EE(Project)/Ynk Zone/WO/105/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 12-03-2019

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 12-03-2019

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	19	19	1.9	98.1	90-100	90-100	90-100	95-100
3	2.36 mm	45	64	6.4	93.6	60-95	75-100	85-100	95-100
4	1.18 mm	228	292	29.2	70.8	30-70	55-90	75-100	90-100
5	600 micron	193	485	48.5	51.5	15-34	35-59	60-79	80-100
6	300 micron	217	702	70.2	29.8	5-20	8-30	12-40	15-50
7	150 micron	205	907	90.7	9.3	0-10	0-10	0-10	0-15
8	Pan	93	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-07-06-22** **Date: 14-03-2019**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.53	–
2	Specific Gravity	2.54	–
3	Material finer than 75 micron(%)	6.1	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2019-07-06-22**	**Date: 28/03/2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.	
Address	:	Project Sub Division, BBMP, Bangalore.	
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.	
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.	
Customer's Reference	:	EE(Project)/Ynk Zone/WO/105/18-19	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	23-03-2019	
Customer ID	:	PCC	
Sample Type /Size	:	150X150X150 mm	
Sample grade/Age	:	M15 / 7 Days Compressive Strength	
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5	
Date of test	:	28/03/2019	

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	21/03/2019	28/03/2019	149.66 X 149.90 X 149.22	22433	**8.298**	272.7	12.2	12.2
2	PCC	M15	21/03/2019	28/03/2019	149.30 X 151.52 X 151.36	22622	**8.221**	277.5	12.3	
3	PCC	M15	21/03/2019	28/03/2019	151.31 X 150.52 X 151.31	22775	**8.866**	280.7	12.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2019-07-06-22**	**Date: 19/04/2019**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.	
Address	:	Project Sub Division, BBMP, Bangalore.	
Project Name	:	Community Property Maintenance Including Parks in Ward No.03.	
Agency	:	Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.	
Customer's Reference	:	EE(Project)/Ynk Zone/WO/105/18-19	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	23-03-2019	
Customer ID	:	PCC	
Sample Type /Size	:	150X150X150 mm	
Sample grade/Age	:	M15 / 28 Days Compressive Strength	
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5	
Date of test	:	19/04/2019	

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	21/03/2019	19/04/2019	150.55 X 150.29 X 150.71	22627	**8.301**	392.5	17.3	17.5
2	PCC	M15	21/03/2019	18/04/2019	150.66 X 151.02 X 150.89	22752	**8.129**	403.8	17.7	
3	PCC	M15	21/03/2019	18/04/2019	150.08 X 149.27 X 149.16	22403	**8.743**	390.3	17.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID : **CP-2019-07-06-22** **Date: 20-03-2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Community Property Maintenance Including Parks in Ward No.03.

Agency : Sri.Charan N S, No.186, 9th Cross, CIL Layout, Cholanayakanahalli, RT Nagar, Bangalore-32.

Customer's Reference : EE(Project)/Ynk Zone/WO/105/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-03-2019

Sample Type /Size : CC Kerb Stone/ 450*165*400mm

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 16/03/2019

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.01	165.51	2.864	7854	142.1	18.1	18.1	22.6
2	B	100.03	165.49	2.793	7857	145.2	18.5	18.5	23.1
3	C	100.01	165.50	2.815	7854	145.1	18.5	18.5	23.1

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com